

Table 1: Significant Assay Intervals in the Santo Tomas 2021-2022 Program, Holes N027 to N031 and B006 to B007:

Drill Hole No.	Dip	From (m)	To (m)	Length (m)	Cu %	Mo %	Au g/t	Ag g/t*	CuEQ %
N027	-55	17.0	212.2	195.2	0.41	0.003	0.049	3.56	0.45
"	-55	214.2	332.0	117.8	0.22	0.005	0.014	1.70	0.25
N028	-55	55.0	187.0	132.0	0.40	0.007	0.032	3.09	0.46
"	-55	231.0	267.0	36.0	0.20	0.004	0.010	2.22	0.22
N029	-65	249.0	355.1	106.1	0.31	0.010	0.018	2.31	0.36
"	-65	365.3	378.8	13.5	0.25	0.006	0.011	1.74	0.28
"	-65	408.1	420.0	11.9	0.12	0.016	0.016	1.09	0.19
N030	-55	52.5	264.0	211.6	0.41	0.003	0.065	2.42	0.47
"	-55	269.2	287.0	17.8	0.22	0.010	0.072	1.62	0.31
"	-55	317.0	450.0	133.0	0.17	0.003	0.010	1.43	0.19
N031	-55	125.0	284.6	159.6	0.32	0.008	0.032	1.80	0.37
"	-55	292.0	326.4	34.4	0.26	0.004	0.009	1.43	0.28
B006	-55	409.0	426.9	17.9	0.31	0.001	0.040	3.69	0.35
"	-55	478.0	490.0	12.0	0.15	0.001	0.024	2.37	0.17
B007	-55	488.0	716.0	228.0	0.31	0.007	0.051	2.36	0.37

Cu Equivalent (CuEq) % = Cu % + (Mo %*3.75) + (Au ppm*0.752). The commodity prices (3-year Average) used are in \$US: Cu \$3.20 /lb, Mo \$12.00 /lb, and Au \$1,650.00 /troy oz. * Ag values are not used in the CuEq calculations.





Plate 50

Section Alignment Line




SANTO TOMAS PROJECT

Oroco Resource Corp.


Plate 50: North Zone Cross-Section


Looking Towards N 020° East

Holes N017, N031 Cu and CuEQ




SANTO TOMAS PROJECT
Oroco Resource Corp.
Plate 55: North Zone Cross-Section
Looking Towards N 020° East
Holes N008,N018,N030 Cu and CuEq





SANTO TOMAS PROJECT
Oroco Resource Corp.
Plate 59: North Zone Cross-Section
Looking Towards N 020° East Holes
N001,N025,N029 Cu & CuEq



SANTO TOMAS PROJECT
Oroco Resource Corp.
Plate 68: North Zone Cross-Section
Looking Towards N 020° East
Hole N028 Cu and CuEq

